## **BEMO PMC Ceiling Systems**

Panel and Pattern Specifications





**Finishes:** Materials are pretreated, primed and, roller-coil coated with a 1.0 mil total dry film thickness (.2 mil primer with a .8 mil topcoat). The reverse side is coated with a wash coat of .4 to .5 mil dry film thickness.

More than **20 standard colors** are available, plus **6 premium colors** (special order). A variety of wood grain and mill finishes are also available. Ask your Bemo representative for details.



## Bemo USA Corporation

1755 N. 48th Street, Mesa, Arizona USA 85205 | 480-545-7900

visit www.bemousa.com. For more information call or email at techservices@bemousa.com.